



**ELSID**  
CARBON ENGINEERING

## **CALCINED COKE**

### **0.2 - 4 mm**

<b>PARAMETERS</b>	<b>UNITS.</b>	<b>SPECIFICATIONS</b>	<b>TEST METHOD</b>
<b>FIX CARBON</b>	<b>%</b>	<b>99.5</b>	<b>ASTM D 7582</b>
<b>ASH</b>	<b>%</b>	<b>0.35</b>	<b>DIN 51903</b>
<b>SULFUR</b>	<b>%</b>	<b>0.7</b>	<b>ASTM D 4239</b>
<b>MOISTURE</b>	<b>%</b>	<b>0.2</b>	<b>ISO 11412</b>
<b>VOLATILES</b>	<b>%</b>	<b>0.15</b>	<b>ISO 9406</b>

<b>GRANULOMETRY (mm)</b>	<b>UNITS.</b>	<b>SPECIFICATIONS</b>
<b>&gt;4</b>	<b>%</b>	<b>0</b>
<b>4-1</b>	<b>%</b>	<b>70</b>
<b>&lt;0.2</b>	<b>%</b>	<b>2</b>

ELSID SA, 15H Nufarului Street, 077165, Snagov, Ilfov, Romania

T: +4 031 437 00 33 / +4 031 437 00 38 ; F: +4 031 438 17 09

[www.elsid.ro](http://www.elsid.ro)